



RANGE NAME	<b>Terre</b>
SHAPE	<b>Standard 400x400x30</b>
COLOURS	<b>Marigold, Sinia Pearl, Oryx</b>

PROPERTIES & SPECIFICATIONS	
WORK SIZE DIMENSIONS (LENGTH X WIDTH X HEIGHT MM)	400x400x30
DIMENSIONAL CATEGORY	DPA2
AVERAGE WEIGHT (KG)	12.924
AVERAGE NUMBER PER TONNE	77.40000000000001
NUMBER PER M <sup>2</sup>	6.25
NUMBER PER PALLET	
CHARACTERISTIC BREAKING LOAD (kN)	8
MEAN COLD WATER ABSORPTION (%)	
MEAN ABRASION RESISTANCE (CM <sup>3</sup> )	
SLIP RESISTANCE CATEGORY	P4

AM-P- SQLD-000157

Tested as per AS/NZS 4456: 2003 and 4586: 2013.

This data represents average results from commercial production lots and is for general description purposes only. Figures are accurate at date of publication and subject to change without notice. Contact Austral Masonry for confirmation of product specification. December 2013



RANGE NAME	<b>Terre</b>
SHAPE	<b>Standard 600x400x30</b>
COLOURS	<b>Marigold, Sinia Pearl, Oryx</b>

PROPERTIES & SPECIFICATIONS	
WORK SIZE DIMENSIONS (LENGTH X WIDTH X HEIGHT MM)	600x400x30
DIMENSIONAL CATEGORY	DPA2
AVERAGE WEIGHT (KG)	18.442
AVERAGE NUMBER PER TONNE	54.2
NUMBER PER M <sup>2</sup>	4.166
NUMBER PER PALLET	
CHARACTERISTIC BREAKING LOAD (kN)	5.3
MEAN COLD WATER ABSORPTION (%)	
MEAN ABRASION RESISTANCE (CM <sup>3</sup> )	
SLIP RESISTANCE CATEGORY	P4

AM-P- SQLD-000160

Tested as per AS/NZS 4456: 2003 and 4586: 2013.

This data represents average results from commercial production lots and is for general description purposes only. Figures are accurate at date of publication and subject to change without notice. Contact Austral Masonry for confirmation of product specification. December 2013



RANGE NAME	Terre
SHAPE	Standard Unit 1400x1400x30
COLOURS	Marigold French Pattern

PROPERTIES & SPECIFICATIONS	
WORK SIZE DIMENSIONS (LENGTH X WIDTH X HEIGHT MM)	1400x1400x30
DIMENSIONAL CATEGORY	DPA2
AVERAGE WEIGHT (KG)	
AVERAGE NUMBER PER TONNE	
NUMBER PER M <sup>2</sup>	
NUMBER PER PALLET	
CHARACTERISTIC BREAKING LOAD (kN)	
MEAN COLD WATER ABSORPTION (%)	
MEAN ABRASION RESISTANCE (CM <sup>3</sup> )	
SLIP RESISTANCE CATEGORY	P4

AM-P- SQLD-000161

Tested as per AS/NZS 4456: 2003 and 4586: 2013.

This data represents average results from commercial production lots and is for general description purposes only. Figures are accurate at date of publication and subject to change without notice. Contact Austral Masonry for confirmation of product specification. December 2013